



TAAM OIL AND GAS TRADING

BITUMEN 50-70

PRODUCT SPECIFICATION :				BITUMEN	50-70
DATE :	1/24/2024	Laboratory Enviroment Condition			
BACH NO :		TEMPRATURE :		25	©
SAMPLE No :	1063	HUMIDITY :		38	%
PROPERTY	UNIT	ACCEPTANCE		TEST METHOD	TEST RESULT
		MIN	MAX		
Penetration at 25°C-100g-5S	0.1mm	50	70	ASTM D-5	66
Softening Point (°C)	°C	46	-	ASTM D-36	49.6
Flash Point (°C)	°C	230	-	ASTM D-92	323
Kinematic Viscosity@135°C	cst	250	-	ASTM D-2170	336
Ductility, 25°C	cm	100	-	ASTM D-113	>100
Drop in penetration After Heating	%	-	20	ASTM D-6 & ASTM D-5	6.7
Loss on Heating (WT%)	%	-	0.5	ASTM D-6	0.06
Solubility in TCE	%	99	-	ASTM D-2042	99.93
Solubility in TCE	-	-	-	*A.A.S.H.O T102	NEGATIVE
Fraass Braking Point	-	3	6	EN12593	4
Specific Gravity at 25/25°C		1.01	1.06	ASTM D-70	1.027
PACKAGING METHOD :					
<p>1-1000 KG. Jumbo bag or poly bag , double layer bag with an outer layer of polypropylene and an inner layer of naylon.</p> <p>2- 300 KG. Jumbo bag or poly bag , double layer bag with an outer layer of polypropylene and an inner layer of naylon.</p> <p>3- bulk carriage is available .</p> <p>4- Barrel carriage is available.</p>					
STORAGE AND HANDLING RECOMMENDATION :					
<p>1-store in unopened containers.</p> <p>2- Storage temperature limit 1°C - 50°C for normal operations, such as blending and transferring liquid bitumen temperature 10°C - 40°C above the minimum pumping temperature are recommended</p>					
RECOMMENDED APLICATION TEMPRATURE :					
<p>1-Asphalt Mixing Temprature : 150-160 °C</p> <p>2-Asphalt Compaction temprature : 135-145 °C</p>					